

**Sidewalk Maintenance Standards
Effective February 1, 1984**

DEFECTIVE SIDEWALK SAMPLES

Any public sidewalk exhibiting one or more of the following characteristics:

- (a) Vertical Separation (b) Horizontal Separation (c) Holes or Depressions**
- (d) Spalling (e) Cracked (f) Missing Parts (g) Deviation**

**(a) Vertical separations equal to three-fourths
(3/4) inch or more.**



**(b) Horizontal separations equal to three-fourths
(3/4) inch or more.**



(c) Holes or depressions equal to three-fourths (3/4) inch or more.

(d) Spalling over fifty (50) percent of a single square or panel of sidewalk with one or more depressions equal to one-half (1/2) inch or more.



(e) A single square or panel of sidewalk cracked in such a manner that no part thereof has a piece greater than one (1) square foot, or is cracked in such a manner that it constitutes danger or potential danger to the public.



(f) A sidewalk with any part there of missing to the full depth.



(g) A deviation on the staked and constructed grade equal to three-fourths (3/4) inch or more.

